

**Amendments to the Specification:**

Please amend the paragraph at page 6, lines 29-34 as follows:

A coating solution is prepared by successively adding Eudragit® RS 30 D (methacrylic acid copolymer), triethyl citrate, talc and Aerosil® R 972 (hydrophobic silica) to the purified water. The chemical name of Eudragit® RS 30 D is poly(ethyl acrylate, methyl methacrylate, trimethylammonioethyl methacrylate chloride) 1:2:0.1. Stirring of the suspension is maintained until the mixture is homogeneous, and then throughout the coating.